



AREA:

GENERAL

CONDITION:

Inside or outside rubber of tyre is deteriorated by oil or chemicals. (Rubber swells, becomes tacky or shredded.)



CAUSES:

- Contamination by oil or chemicals during tyre storage or when vehicle is parked.
- Use some non-authorized puncture sealants.

RECOMMENDATIONS:

- Keep tyres away from oil or chemicals.
- Do not use non-authorized puncture sealants.

HOW TO CHECK:

Inspect tyre tread and sidewall for abnormal swellings (tread will be soft and tacky).